

Bondstrand® Series 4000 Fiberglass Pipe and Fittings for General Industrial Service

Scope

Bondstrand Series 4000 pipe and fittings are available in 1"-16" diameters. The specification defines the reinforced thermosetting resin (RTR) piping system to be used in those sections of plant piping, general services, calling for fiberglass piping systems.

References, Quality Assurance

References are made to other standards and tests which are a part of this section as modified. Where conflict exists between the requirements of this specification and listed references, the specification shall prevail.

Physical and Mechanical Properties

Pipe Property	Units	70°F (21°C)	200°F (93°C)	ASTM Method
Circumferential Tensile Stress at Weeping	10 ³ psi MPa	18.50 128.00	- -	D1599
Tensile Modulus	10 ⁶ psi GPa	3.65 25.20	3.20 22.10	
Poisson's Ratio		0.56	0.68	D2105
Longitudinal Tensile Strength	10 ³ psi MPa	8.50 58.60	6.90 47.60	D2105
Tensile Modulus	10 ⁶ psi GPa	1.60 11.10	1.24 8.60	D2105
Poisson's Ratio		0.37	0.41	D2105
Beam Apparent-Elastic Modulus	10 ⁶ si GPa	1.70 11.70	1.08 6.90	D2925
Hydrostatic Design Basis (Cyclic)	10 ³ psi MPa	6.00 11.40	- -	D2992
Thermal Conductivity Pipe Wall	Btu•in/(hr•ft ² •°F) W/m•C	1.70 0.25	- -	C177
Thermal Expansion Linear	10 ⁻⁶ in/in/°F 10 ⁻⁶ mm/mm°C	8.50 15.30	- -	D696
Flow Coefficient	Hazen-Williams	150.00	-	
Absolute Roughness	10 ⁻⁶ ft	17.40 5.30	-	
Specific Gravity	-	1.80	-	D792
Density	lb/in ³	0.07	-	

Performance Requirements

Pipe shall be manufactured according to ASTM D2996 Specification for RTRP. When classified under ASTM D2310, the pipe shall meet Type I, Grade I and Class F (RTRP 11FE) cell limits in 2" through 16" nominal pipe sizes.

The piping systems must meet USFDA requirements for food processing piping under Federal Regulations 21CFR 175.105 and 21CFR 177.242 when bonded with RP6B adhesive.

Materials

Pipe Construction

Filament-wound fiberglass reinforced epoxy resin pipe shall be Bondstrand® 4000 as manufactured by NOV Fiber Glass Systems or approved equal. The integral reinforced corrosion barrier shall have a nominal 50-mil thickness and be constructed with the same epoxy resin as the pipe structural wall.

Structural Wall

The pipe shall have the following nominal wall thickness.

Diameter	Nominal Wall Thickness	
	in	mm
2	.123	3.1
3	.126	3.2
4	.151	3.8
6	.181	4.6
8	.226	5.7
10	.226	5.7
12	.226	5.7
14	.250	6.4
16	.269	6.8

Pipe End Preparation Options

The piping manufacturer will provide 20' or 30" random length joints if the contractor requests them in sizes 2"-6" to reduce field labor time in those sections of the system where longer lengths may be employed. Additionally, the pipe manufacturer will provide pipe joints with the spigot ends already prepared for adhesive application to reduce field labor time on all pipe sizes (2"-16").

Pressure Rating

Aromatic amine cured epoxy resin piping shall be rated for a minimum of 150 psi at 200°F in sizes through 16".

Fittings

It is important to maintain compatibility of fittings, piping and adhesives to ensure that the system performs as specified. Pipe, fittings and adhesive shall be supplied by the same manufacturer.

Filament wound fittings in 1"-16" sizes shall be filament wound with a reinforced, resin-rich liner of equal or greater thickness than the pipe liner and shall be manufactured with the same resin type as the pipe.

Compression molded fittings in sizes 2"-6" may be used in some services; contact manufacturer. Where fast closure of valves may produce surges (water hammer), filament-wound fittings will be used. Contact molded, spray up or hand lay-up fittings shall not be allowed.

Testing

Inspection and testing of the piping will be performed in accordance with the requirements of ANSI B31.1. Hydrostatic testing of all installed piping shall be performed with water at a maximum of 1-1/2 times the system design pressure or of the lowest rated piping system component, whichever is lower.

Installation

Installation and techniques, as well as system design criteria including burial, anchoring, guiding and supporting, shall be in accordance with manufacturer's recommendations. Piping system installers and fitters will be trained by a direct factory employee of the piping system manufacturer and certified by the trainer prior to system assembly in the field.

National Oilwell Varco has produced this brochure for general information only, and it is not intended for design purposes. Although every effort has been made to maintain the accuracy and reliability of its contents, National Oilwell Varco in no way assumes responsibility for liability for any loss, damage or injury resulting from the use of information and data herein nor is any warranty expressed or implied. Always cross-reference the bulletin date with the most current version listed at the website noted in this literature.

North America
17115 San Pedro Ave. Suite 200
San Antonio, Texas 78232 USA
Phone: 210 477 7500

South America
Estrada de Acesso á Zona
Industrial Portuária de Suape s/no.
Recife, Brazil 55.590-000
Phone: 55 31 3501 0023

Europe
P.O. Box 6, 4190 CA
Geldermalsen, The Netherlands
Phone: 31 345 587 587

Asia Pacific
No. 7A, Tuas Avenue 3
Jurong, Singapore 639407
Phone: 65 6861 6118

Middle East
P.O. Box 17324
Dubai, UAE
Phone: 971 4881 3566

www.fgspipe.com • fgspipe@nov.com

The logo for NOV Fiber Glass Systems, featuring the letters 'NOV' in a stylized font followed by 'Fiber Glass Systems' in a bold, sans-serif font.

© 2013, NATIONAL OILWELL VARCO
® Trademark of NATIONAL OILWELL VARCO
CI4001 April 2013